



Designation: B159/B159M – 17

## Standard Specification for Phosphor Bronze Wire<sup>1</sup>

This standard is issued under the fixed designation B159/B159M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification establishes the requirements for round and flat (square and rectangular) phosphor bronze wire of UNS Alloy Nos. C51000, C52100, and C52400 for general and spring applications.

1.1.1 Rectangular and square wire of the three alloys are generally available in sizes up to a maximum of 0.188 in. [5 mm] thick and 1.250 in. [32 mm] wide.

1.1.2 Round wire from Copper Alloy UNS No. C51000 is generally available in sizes up to 0.500 in. [13 mm] in diameter.

1.2 *Units*—The values stated in either inch-pound units or in SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

1.3 Additional requirements for these products are established in Specification **B250/B250M**, see Section 3.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—It is to be understood that this specification is general. Since the product is used for many applications where the requirements of the operations used are too particular to be specified by any of the ordinary mechanical tests, it is frequently advisable to submit samples or drawings to the manufacturer and secure an adjustment of temper to suit the actual application for which the product is intended.

NOTE 2—Product in rod, bar and shape form is produced to Specification **B139/B139M**.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the*

*Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**B139/B139M** Specification for Phosphor Bronze Rod, Bar, and Shapes

**B250/B250M** Specification for General Requirements for Wrought Copper Alloy Wire

**B601** Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

**B846** Terminology for Copper and Copper Alloys

**B950** Guide for Editorial Procedures and Form of Product Specifications for Copper and Copper Alloys

**E8/E8M** Test Methods for Tension Testing of Metallic Materials

**E62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)<sup>3</sup>

**E290** Test Methods for Bend Testing of Material for Ductility

**E478** Test Methods for Chemical Analysis of Copper Alloys

### 3. General Requirements

3.1 The following sections of Specification **B250/B250M** are a part of this specification:

3.1.1 Terminology;

3.1.2 Materials and Manufacture;

3.1.3 Workmanship, Finish, and Appearance;

3.1.4 Sampling;

3.1.5 Number of Tests and Retests;

3.1.6 Specimen Preparation;

3.1.7 Test Methods;

3.1.8 Significance of Numerical Limits;

3.1.9 Inspection;

3.1.10 Rejection and Rehearing;

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Oct. 1, 2017. Published December 2017. Originally approved in 1941. Last previous edition approved in 2011 as B159/B159M – 11. DOI: 10.1520/B0159\_B0159M-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard



- 3.1.11 Certification;
- 3.1.12 Test Reports;
- 3.1.13 Packaging and Package Markings; and
- 3.1.14 Supplementary Requirements.

3.2 In addition, when a section with a title identical to one of those referenced in **3.1** appears in this specification, it contains additional requirements which supplement those appearing in Specification **B250/B250M**.

#### 4. Terminology

##### 4.1 Definitions of Terms Specific to This Standard:

4.1.1 *cast, n*—The maximum diameter of coiled wire when one complete circumference rests completely on a flat surface such as a table, workbench, or floor.

4.1.2 *camber offset, n*—The axial component of curvature of wire in an unrestrained state.

4.1.2.1 *Discussion*—The camber is measured as the offset in the ends of one turn of freely hanging wire.

4.2 For other definitions of terms related to copper and copper alloys, refer to Terminology **B846**.

#### 5. Ordering Information

5.1 Include the following specified choices when placing orders for product under this specification, as applicable:

5.1.1 ASTM designation and year of issue (for example, B159/B159M – XX),

5.1.2 Copper Alloy UNS No. (for example, C51000),

5.1.3 Temper designation (Section 8),

5.1.4 Dimensions (diameter, distance between parallel surfaces, and so forth),

5.1.5 Type of edge (square corners, rounded corners, and so forth),

5.1.6 How furnished (coil spool, reel, specific lengths, and so forth), and

5.1.7 Intended application.

5.2 The following options are available but may not be included unless specified at the time of placing of the order, when required:

5.2.1 Heat identification or traceability details;

5.2.2 Certification;

5.2.3 Test Reports;

5.2.4 Special packaging and package markings;

5.2.5 Tolerances for cast and camber offset, if specified;

5.2.6 If product is purchased for agencies of the U.S. Government (see Section 11);

5.2.7 Formability requirements other than bending (see **10.1.2**); and

5.2.8 Requirements and method for determining cast and camber offset (**12.1.8**).

#### 6. Materials and Manufacture

##### 6.1 Materials:

6.1.1 The material of manufacturer shall be a cast billet of Copper Alloy UNS No. C51000, C52100, or C52400 of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 When specified in the contract or purchase order that heat identification or traceability is required, the purchaser shall specify the details desired.

##### 6.2 Manufacture:

6.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing processes as to produce a uniform wrought structure in the finished product which will meet the temper properties specified.

#### 7. Chemical Composition

7.1 The material shall conform to the chemical composition requirements of **Table 1** for the Copper Alloy UNS No. specified in the ordering information.

7.1.1 These composition limits do not preclude the presence of other elements. When required, limits may be established and analysis required for unnamed elements by agreement between the supplier and the purchaser.

7.2 Copper listed as the “remainder” is the difference between the sum of results for all elements determined and 100 %.

7.3 When all elements listed in **Table 1** are determined, the sum of results shall be 99.5 % min.

#### 8. Temper

8.1 Tempers, as defined in Classification **B601**, available under this specification are O61 (annealed), H01 (¼ hard), H02 (½ hard), H03 (¾ hard), H04 (hard), H06 (extra hard), H08 (spring), and H10 (extra spring).

8.1.1 Tempers not covered by this specification shall be by agreement between the purchaser and supplier.

NOTE 3—The purchaser shall confer with the supplier for availability of product in specific alloy, temper, form, and size.

#### 9. Mechanical Property Requirements

##### 9.1 Tensile Strength Requirements:

9.1.1 When tested in accordance with Test Methods **E8/E8M**:

9.1.1.1 Round and square wire for general application produced from Copper Alloy UNS Nos. C51000, C52100, and C52400 shall conform to the requirements prescribed in **Table 2**.

9.1.1.2 Round or square wire produced from Copper Alloy UNS No. C51000 in H08 (spring) temper shall conform to the requirements prescribed in **Table 3**.

9.1.1.3 Rectangular wire produced from Copper Alloy UNS Nos. C51000, C52100, and C52400 shall conform to the requirements prescribed in **Table 4**.

**TABLE 1 Chemical Requirements**

Copper Alloy UNS No.	C51000	C52100	C52400
	Composition, %		
Copper, incl silver	remainder	remainder	remainder
Lead, max	0.05	0.05	0.05
Iron, max	0.10	0.10	0.10
Tin	4.2–5.8	7.0–9.0	9.0–11.0
Zinc, max	0.30	0.20	0.20
Phosphorus	0.03–0.35	0.03–0.35	0.03–0.35

**TABLE 2 Mechanical Requirements for Round or Square Wire for General Purposes**

Temper Designation		Tensile Strength, ksi [MPa] <sup>A</sup>		
Code	Name	Copper Alloy UNS No.		
		C51000	C52100	C52400
O61	annealed	48–63 [330–435]	53–68 [365–470]	60–75 [415–515]
H01	quarter-hard	60–76 [415–525]	74–91 [510–625]	83–102 [570–705]
H02	half-hard	80–97 [550–670]	95–115 [655–795]	108–129 [745–890]
H03	three-quarter-hard	96–115 [660–795]	113–135 [780–930]	125–148 [860–1020]
H04	hard	108–128 [745–885]	125–150 [860–1035]	135–160 [930–1105]
H08	spring	see Table 3	...	...

<sup>A</sup> ksi = 1000 psi.**TABLE 3 Mechanical Requirements for H08 (Spring Temper) UNS No. C51000 Round or Square Wire**

Diameter or Distance Between Parallel Surfaces, in. [mm]	Tensile Strength, min, ksi [MPa] <sup>A</sup>	Elongation in 2 in. [50 mm] min, %
0.025 [0.60] and under	145 [1000]	...
Over 0.025 to 0.0625 [0.060 to 1.6]	135 [930]	...
Over 0.0625 to 0.125 [1.6 to 3.0]	130 [895]	...
Over 0.125 to 0.250 [3.0 to 6.0]	125 [860]	...
Over 0.250 to 0.375 [6.0 to 10]	120 [825]	5.0
Over 0.375 to 0.500 [10 to 16], incl	105 [725]	9.0

<sup>A</sup> ksi = 1000 psi.**TABLE 4 Mechanical Requirements for Rectangular Wire (Other Than Square Wire)**

Temper Designation		Tensile Strength, ksi [MPa] <sup>A</sup>		
Code	Name	Copper Alloy UNS No.		
		C51000	C52100	C52400
O61	annealed	43–58 [295–400]	53–67 [365–460]	58–73 [400–505]
H02	half-hard	58–73 [400–505]	69–84 [475–580]	76–91 [525–625]
H04	hard	76–91 [525–625]	85–100 [585–690]	94–109 [650–750]
H06	extra hard	88–103 [605–710]	97–112 [670–770]	107–122 [740–840]
H08	spring	95–110 [655–760]	105–119 [725–820]	115–129 [795–890]
H10	extra spring	100–114 [690–785]	116–122 [800–840]	120–133 [825–915]

<sup>A</sup> ksi = 1000 psi.

## 10. Performance Requirements

### 10.1 Bending Requirements:

10.1.1 Wire in sizes up to 0.250 in. [7 mm] inclusive produced from Copper Alloy UNS No. C51000 shall withstand being bent cold (room temperature) through an angle of 120°

on a radius equal to the diameter or distance between parallel surfaces in accordance with Test Methods E290. When so bent, tempers H08 and H10 shall not develop cracks or other flaws visible to the unaided eye on the outside surface of the bend.

10.1.2 Other formability requirements, when specified, shall be as agreed upon between purchaser and supplier.

## 11. Purchases for U.S. Government

11.1 Product purchased for agencies of the U.S. Government shall conform to the additional requirements prescribed in the Supplementary Requirements section of Specification B250/B250M (see Section 11).

## 12. Dimensions, Mass, and Permissible Variations

12.1 The dimensions and tolerances for product produced to this specification shall be as specified in the following tables and related paragraphs or specified titles found in Specification B250/B250M:

12.1.1 *Diameter or Distance Between Parallel Surfaces*—Table 2.

12.1.2 *Thickness*—Table 4.

12.1.3 *Width*—Table 6.

12.1.4 *Length (Flat Wire Product)*—Tables 7 and 8.

12.1.5 *Straightness (Flat Wire Product)*—Table 9.

12.1.6 *Edge Contours*—Edge Contour section.

12.1.7 *Corner Radius*—Figure 4.

12.1.8 *Cast and Camber Offset*—When specified, the requirements and method shall be as agreed upon between the purchaser and supplier.

## 13. Test Methods

### 13.1 Chemical Analysis:

13.1.1 In cases of disagreement, test methods for chemical analysis shall be subject to agreement between the manufacturer or supplier and the purchaser. The following table is a list of published methods, some of which may no longer be viable, which along with others not listed, may be used subject to agreement:

Element	Test Methods
Copper	E478
Phosphorus	E62
Lead	E478 (AA)
Iron	E478
Zinc	E478 (Titrimetric)
Tin	E478

13.1.2 Test method(s) to be followed for the determination of elements required by contractual or purchase order agreement shall be as agreed upon between the supplier and the purchaser.

## 14. Keywords

14.1 phosphor bronze alloy wire; UNS No. C51000 wire; UNS No. C52100 wire; UNS No. C52400 wire



## **SUMMARY OF CHANGES**

Committee B05 has identified the principal changes to this specification that have been incorporated since the 2011 issue as follows:

(1) Minor editing throughout in accordance with Guide **B950**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*

This file is provided by Boedon Industech Co., Ltd. and available for download to our clients.

Boedon is a professional special alloy wire weaving and filter element company, for more technical supports, resources and quotations, please visit:

[www.boedon.com](http://www.boedon.com)

Contact: +86-318-5111380

WhatsApp: +86-18931820567